

TECHNICAL SHEET
PSO EXR DAKAR 45X45 EXT 2.03

EVALUATED CHARACTERISTICS	TEST METHOD	NORM ISO 13006 REQUIREMENTS (BIIB)	RESULT	CONCLUSION
DIMENSIONS AND SURFACE QUALITY				
* Length and Width, mm Manufacturing Size: 451.0 mm Average Size: 451.7 mm	ISO 10545-2	± 0.6%; ± 2.0mm	(%) (mm) 0.16 0.70	Comply
* Thickness, mm Manufacturing: 7.5 mm Average result: 7.6 mm	ISO 10545-2	± 5.0%; ± 0.5mm	1.33 0.10	Comply
* Straightness of sides, %	ISO 10545-2	± 0.5%; ± 1.5mm	0.04 0.20	Comply
* Rectangularity, %	ISO 10545-2	± 0.5%; ± 2.0mm	0.16 0.70	Comply
* Surface flatness Edge curvature, %		± 0.5%; ± 2.0mm	0.07 -0.04 0.30 -0.20	Comply
Centre curvature, %	ISO 10545-2	± 0.5%; ± 2.0mm	0.13 0.00 0.80 0.00	Comply
Warpage, %	ISO 10545-2	± 0.5%; ± 2.0mm	0.14 -0.05 0.90 -0.30	Comply
* Surface quality, %	ISO 10545-2	A minimum of 95 % of the tiles are to be free from visible defects which can impair the appearance of a major area of tiles	97.5%	Comply
PHYSICAL PROPERTIES				
* Water absorption (E _v), %	ISO 10545-3	6 % < E _v ≤ 10 % Individual maximum 11 %	6.5 6.7	Comply Comply
* Breaking strength, N (Thickness ≥ 7.5 mm)	ISO 10545-4	Not less than 800	955	Comply
* Modulus of rupture, N/mm ²	ISO 10545-4	Minimum 18 Individual minimum 16	28 26	Comply Comply
* Abrasion resistance - CU	ISO 10545-7	Report abrasion class and cycles passed	Class 4 Cycles 2100	-
* Crazeing resistance	ISO 10545-11	Required	No crazeing	Comply
CHEMICAL PROPERTIES				
* Resistance to staining - Green Oxide	ISO 10545-14	Minimum class 3	Class 5	Comply
- Iodo	ISO 10545-14	Minimum class 3	Class 5	Comply
- Olive oil	ISO 10545-14	Minimum class 3	Class 5	Comply
* Resistance to low concentrations of acids and alkalis - 3% Hydrochloric Acid (V / V)		Manufacturer is to state classification	LB	-
- Potassium hydroxide, 30 g / l			LA	-
* Resistance to high concentrations of acids and alkalis - 18% Hydrochloric Acid (V / V)	ISO 10545-13	Test method available	HB	-
- Potassium hydroxide, 100 g / l			HA	-
* Resistance to household chemicals and swimming pool salts - Ammonium Chloride 100 g / l		Minimum B	A	Comply
- Sodium hypochlorite, 20 mg / l	ISO 10545-13		A	Comply
<p>Requirements verified as indicated in the INTERNATIONAL STANDARD, ISO 13006 "Ceramic Tiles - Definitions, Classification, Characteristics and marking", Annex k (normative), Table k,1. Dry-pressed ceramic tiles 6 % < E_v ≤ 10 % Group BIIB₆ The weight, tone and dimensions are subject to some of the inevitable variations typical of ceramic firing processes.</p>				
DATE OF ISSUE			Thursday, July 21, 2022	
Prepared by: Quality Supervisor			Reviewed by: Manager Quality Assurance	
César Prado R.			Marlene Chauca R.	